

METHODS AND TOOLS

DETERMINING MERCURY USE IN THE ARTISANAL AND SMALL-SCALE GOLD MINING (ASGM) SECTOR



ARTISANAL
GOLD COUNCIL



Lecture 1 Introduction to ASGM





Introduction to ASGM

Overview




ARTISANAL
GOLD COUNCIL

- What is ASGM?
- Geology and Gold
- Mineral Extraction
- Mineral Processing
- Mercury Use in ASGM
- Gold Supply Chains
- Formality and Governance
- Spatial Distribution & Seasonality
- Health and Environment

What is ASGM?

ASGM (Artisanal and Small Scale Gold Mining):

Gold mining done by individual miners, communities, or small enterprises with limited capital investment and production. ASGM uses largely manual and semi-mechanised techniques.



Where does gold come from?



ARTISANAL
GOLD COUNCIL



Rocks



Minerals



Gold



Where does gold come from?



ARTISANAL
GOLD COUNCIL



gold vein



disseminated gold



gold in surface
sediments




Rock containing gold that is targeted by miners = **gold ore**.


To produce gold, the ore must be processed to remove the other minerals.

Ore Grade

The amount of gold in the ore (expressed in g/T)



lower grade




higher grade

- Range from <1 to >100 g/T
- Can vary significantly between sites, and even within deposits

Gold Purity



ARTISANAL
GOLD COUNCIL



- The “gold” recovered from ore is typically a mix of metals
- **Purity is the proportion of this mix that is gold**
- Expressed in % purity (0 to 100%) or in karats (0 to 24K)
- Can vary significantly between sites and less so within a site

Gold Purity



ARTISANAL
GOLD COUNCIL

Correcting from impure to pure (24K) gold:

Weight of gold x (purity of gold/24K)

e.g., You have 100 g of 18K gold. How many g of pure gold?

$$100 \text{ g} \times 18\text{K}/24\text{K} = 75 \text{ g}$$

100 g of 18K gold is 75 g of 24K gold

Mineral Deposits



**Hard Rock
Deposits**

(Primary Deposits)



**Soft Rock
Deposits**

(Alluvial Deposits)

Extraction – Hard Rock



ARTISANAL
GOLD COUNCIL




Open Pit



Mine Shaft

Extraction – Hard Rock



ARTISANAL
GOLD COUNCIL



Extraction – Soft Rock



ARTISANAL
GOLD COUNCIL



Extraction – Soft Rock



ARTISANAL
GOLD COUNCIL



Processing



ARTISANAL
GOLD COUNCIL

Crush

Mill

Concentrate

Amalgamate with Mercury



Burn
Amalgam

Smelt/
Refine




Processing



ARTISANAL
GOLD COUNCIL

Crushing *Reduces size of ore rocks*



Manual Hammering



Jaw Crusher



Hammer Crusher



Milling

Reduces grain size further. Liberates gold from other minerals in the ore.



Good Liberation: grain size of the ore is fine enough to separate gold particles from other minerals.

** Proper grain size varies with ore.*





Grain size Control

Improves recovery by ensuring the proper grain size for the best liberation of gold has been achieved.




Processing



ARTISANAL
GOLD COUNCIL

Gravimetric Concentration

Removes non-gold minerals from the milled material, reducing the total volume of the milled ore and concentrating the gold particles within it.



Pan



Sluice



Shaking Table

Processing



ARTISANAL
GOLD COUNCIL


Smelting and Refining

Melts concentrated ore or gold into a solid gold piece. The gold can be further refined (usually by a gold shop or refinery) to pure 24K gold.





Where is mercury used in ASGM?



- Mercury is added to ore to extract gold
- Mercury binds easily with gold, making a heavy mercury-gold amalgam that is easier to separate from the rest of the ore



“AMALGAMATION”

Mercury is added to ore to extract gold



Mercury Amalgamation



ARTISANAL
GOLD COUNCIL

Mix mercury
with ore



Recover
amalgam
(squeeze)



Vaporize
mercury



Sponge gold






Whole Ore Amalgamation





Concentrate Amalgamation



“Mercury use” in ASGM in a Minamata context means:

The net loss of mercury during ore processing

or in other words, the amount of mercury that is lost to the environment during ore processing operations.

Where is mercury lost to the environment?

Mercury Use (loss to environment)

Mix Mercury
With ore



Recover
Amalgam




Vaporize
Mercury




Sponge Gold




Mercury Use (loss to environment)



Mercury Use (loss to environment)



Mercury Use (loss to environment)



Processing



ARTISANAL
GOLD COUNCIL

Processing Tailings (waste)

If waste rock contains enough gold, it is sometimes reprocessed by leaching with cyanide. (worst practice banned by Minamata)



A typical workflow



ARTISANAL
GOLD COUNCIL



A typical workflow



ARTISANAL
GOLD COUNCIL



A typical workflow



ARTISANAL
GOLD COUNCIL



A typical workflow



A typical workflow



A typical workflow



ARTISANAL
GOLD COUNCIL



A typical workflow



A typical workflow




A typical workflow



A typical workflow




ARTISANAL
GOLD COUNCIL



A typical workflow



ARTISANAL
GOLD COUNCIL



Organization of ASGM


Organization of miners



Individuals



Small Businesses



Cooperatives

Primary ASGM workforce - number of workers directly employed in the gold production system (receive direct payment from the gold proceeds).

- miners (extraction workers, processing workers, mining/processing foremen), business owners, mining coordinators, cooperative leaders

Secondary ASGM workforce - number of people indirectly financially dependent on the ASGM sector (provide goods and services to the sector).


- agricultural producers, merchants, traders, service providers

Organization of ASGM



ARTISANAL
GOLD COUNCIL

Distribution of Revenue



Formality / Governance


- Few ASGM operations adhere to national legal frameworks
- Often local governance (Community, Municipality, Local police)
- Understanding the governance structure can provide useful information for inventory work:
 - Understand key stakeholders
 - Determine who to interview
 - Provide insight into local operations



Gold Supply Chain




ARTISANAL
GOLD COUNCIL



Spatial Distribution



ARTISANAL
GOLD COUNCIL



Seasonality



ARTISANAL
GOLD COUNCIL

- ASGM activity can vary greatly throughout the year, especially in regions with a heavy rainy season and seasonal flooding. During these times of the year, productivity and workforce, and thus mercury use in processing may be drastically reduced.

Relevance: Annual mercury use and gold production are often calculated by interviewing about daily productivity. It is important for a researcher to ask clear questions about the seasonality of ASGM in the region so that productivity is not over or underestimated. For example, on Site A, a baseline team finds that 1 kg of Hg is used per day on the site. Miner interviews indicate they work 5 days per week and have 10 holidays per year (250 days of work per year). This would lead the officer to believe: **1 kg Hg/d x 250 d/y = 250 kg Hg/y.**

However, further questioning reveals that all extraction work stops for three months (~60 working days) of the year due to flooding. There are 190 active mining days and the annual mercury use estimate for the site is **1 kg Hg/d x 190 d/y = 190 kg Hg/y.**

Environmental Impact

Tailings (waste) release

To water:

- increased turbidity
- increased erosion
- circulation changes
- coastline alteration
- loss of habitat



To land:

- Loss of habitat
- Loss of mining opportunity



Health Impact

Mercury is a **neurotoxin** – detrimental effects on the nervous system



- Skin contact / absorption
- inhalation




Health



ARTISANAL
GOLD COUNCIL

– ingestion





Summary

- 3 key components of ASGM – each offering important information that can be used for ASGM inventory
 - Extraction
 - Processing
 - Markets
- Must understand each facet of ASGM - each is a source of valuable information
- Significant variation in practices between sites, regions and countries -- approaches will be different in every country and will be tailored to each region within.
- To understand ASGM must embrace its variability



Thank you very much!

Questions?

