UN environment programme

FORESIGHT Brief 034

September 2024

Early Warning, Emerging Issues and Futures

Vehicle tyre particles in the environment

Background

The Foresight Briefs are published by the United Nations Environment Programme (UNEP) to, among others, highlight a hotspot of environmental change, feature an emerging science topic, or discuss a contemporary environmental issue. The public is thus provided with the opportunity to find out what is happening to their changing environment and the consequences of everyday choices, and to think about future directions for policy. The thirty-fourth edition of UNEP's Foresight Briefs looks at the negative effects of tyre abrasion particles and how they can be regulated.

Abstract

Tyre-wear particles are one of the most abundant types of primary microplastics discharged into the environment. During their degradation in the environment, various tyre components are released, including some chemicals with harmful effects to organisms. There are various prevention and mitigation methods that can alleviate the problems, but effectively designed and enforced policies are needed to support these strategies.

Introduction

Driving a vehicle causes abrasion of the tyres, generating very large amounts of small particles, known as tyre-abrasion or tyre-wear particles. These particles are emitted into and spread throughout the environment (Giechaskiel *et al.* 2024; Gieré and Dietze 2022). Due to their chemical composition, typical size, and mode of formation and release, these particles are classified as primary microplastics (Boucher and Friot 2017;

Photo credit: iStock.com / supergenijalac

Hartmann *et al.* 2019; Järlskog *et al.* 2022). Once in the environment, the tyre-wear particles interact with light, air, ozone, and water, as well as with soil, sediments, and biota. These interactions trigger particle degradation, which in turn leads to the release of tyre constituents, including zinc and various organic chemicals (Halsband *et al.* 2020; Gieré and Dietze 2022; Zhang *et al.* 2023). There is increasing evidence that some of these released compounds are highly toxic to various organisms (Brinkmann *et al.* 2022; Chen *et al.* 2023; Bohara *et al.* 2024). It is therefore essential that appropriate measures are taken by both the tyre industry and governments around the world to curtail emission of tyre-wear particles in order to minimize their distribution and concentration in the environment.

Why is this an important issue?

Tyre-wear particles constitute one of the most abundant types of primary microplastics discharged into the environment (Kole *et al.* 2017; Sommer *et al.* 2018; Kole *et al.* 2019; Furuseth and Rødland 2020; Vogelsang *et al.* 2020). It has been estimated, for example, that of the 1.5 million tonnes of primary microplastics reaching the oceans every year, 28 per cent, or 400,000 tonnes, are tyre-wear particles (Boucher and Friot 2017). According to another study, the annual accumulation of tyre-wear particles in the oceans may be as high as 1.0±0.2 million tonnes (PEW Charitable Trusts, 2020). Tyre-wear particles have also been observed within the intestines of fish and other aquatic species (Leads *et al.* 2019; Parker *et al.* 2020), some of which are consumed by humans.

Tyre-wear particles originate from a tyre's outermost layer, known as the tread (Figure 1).



Photo credit: iStock.com / Hitesh Singh. Adapted by UNEP.

Figure 1: Basic structure of a passenger car tyre. Belts provide stiffness to the tread, overall tyre strength, and protection from puncture; body ply maintains tyre shape and prevents it from tearing; beads enable the tyre to firmly grip to the wheel.



Photo credits (a) - (d): Radek Stoček

Figure 2: Images of vehicle tyres that exhibit visible wear of the tread

(a) tyre from passenger car;
(b) tyre from forestry vehicle;
(c) a multi-purpose radial tyre, commonly used for construction vehicles and forklifts; and
(d) commercial tyre, used by vans and heavy-duty vehicles.
Tyre damage caused by fatigue (smooth tread surface – smallest tyre particles generated), abrasion (rougher surface – medium-sized tyre particles generated), and cutting (visible breakage of a large piece from the tread – largest tyre debris generated).



Figure 3: Examples of compositions of a reference passenger car tyre in the European Union (OECD 2014) and of a tyre tread (Winther and Slentø 2010). Colour scheme is identical to that used in Table 1, which provides some details for each of the components shown here. All values given in per cent by mass.

The tread is in direct contact with the road surface and, due to slippage and friction between the two materials, is abraded during driving (Figure 2), especially through acceleration, braking, and cornering (Luhana *et al.* 2004). These particles therefore reflect the chemical composition of the tread rather than that of an entire tyre. Both compositions vary among different manufacturers and tyre types (Gieré *et al.* 2004; Rauert *et al.* 2021). The tyre tread is rich in both natural and synthetic polymers as well as chemical additives, comprises various types of fillers, primarily carbon black and amorphous silica, and does not contain steel or textiles (Figure 3, Table 1) (Gent 2006; Broekhuizen 2024). During tyre manufacturing, certain chemical components, including polycyclic aromatic hydrocarbons (PAHs), are added as unintentional byproducts, because they are associated with carbon black and some chemical additives (e.g., plasticizers) (Boonyatumanond *et al.* 2007; Aatmeeyata and Sharma 2010).

Global release rates of tyre-wear particles have been estimated at approximately 6 million tonnes per year (Kole *et al.* 2017; Kole *et al.* 2019), equivalent to an overall average of 0.8 kilograms (kg) per capita per year. The release rate, however, varies widely among individual countries, reaching values up to about 5 kg/capita/year (Figure 4). Loading the 6 million tonnes of tyre-wear particles onto cargo railroad cars with a capacity of 60 tonnes and a length of 15 metres would create a freight train with a length of 1500 kilometres.

Degradation, or weathering, of tyre-wear particles in the environment or the intestines of wildlife facilitates the release of various chemical compounds, including fillers as well as intentional and non-intentional additives (Evans 1997; Wik and Dave 2009; Wagner *et al.* 2018; Müller *et al.* 2022). Numerous ecotoxicological studies have demonstrated that some of the released chemicals (for example zinc, butadiene, benzothiazoles, PAHs

Table 1. Material classes employed for the fabrication of tyres. For each material class, select compounds are listed as examples with their specific function during production or subsequent use of a tyre (Broekhuizen 2024; Chen *et al.* 2024; Gent 2006; Wan *et al.* 2020)

Material	Type	Examples	Function
Rubber polymers	Natural polymers	Natural rubber (NR)	Provide elastic properties and increase resistance to fatigue and tear; control rolling resistance an traction performance
	Synthetic polymers	Styrene-butadiene rubber (SBR), butadiene rubber (BR), isoprene rubber (IR)	
Fillers	Nanostructured agglomerates	Amorphous silica	Strengthen the rubber to achieve maximum performance and lifespan
		Carbon black	
Fibres and wires	Textile fibre	Nylon, polyester, rayon	Reinforcing the body ply
	Wire cords	Steel	Providing strength to belts and beads
Chemical additives	Zinc oxide and various organic chemicals	Activators and accelerators (e.g. various benzothiazole* compounds	Activate and accelerate chemical reactions during production
		Vulcanizers	Transform rubber into a solid material during production
		Plasticizers	Enhance processability of materials during production
		Antioxidants and antiozonants (e.g. 6PPD**)	Reduce susceptibility to degradation due to exposure to temperature, oxygen and ozone
		Flame retardants	Reduce flammability of rubber

* Benzothiazole: organic chemical compound with the formula C_7H_5NS
** 6PPD: organic chemical compound named N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, and with the formula $C_{18}H_{24}N_2$



Figure 4: Estimated emissions of tyre-wear particles in countries for which data are available. Data given in kilograms per capita per year. Data from Kole *et al*. (2019); Lee *et al*. (2020); Sieber *et al*. (2020); and Prenner *et al*. (2021).

and a substance known as "6PPD"; see Table 1) or their transformation products can cause various biological responses in diverse organisms, including acute toxicity and lethality in some species (Wik and Dave 2006; Wik *et al.* 2009; Halle *et al.* 2020; Halsband *et al.* 2020; Honda and Suzuki 2020; Lu *et al.* 2021; Brinkmann *et al.* 2022; Bohara *et al.* 2024). The potential impact of tyre-wear particles on human health is not well studied, but it can be gender-specific, influenced by social roles, responsibilities, and exposures. For example, women in certain occupations (e.g., street vendors, food-stall cooks, outdoor workers) and children in some school yards may be particularly exposed to pollution from tyres due to prolonged periods spent near busy roads or intersections.

The presence of tyre debris in the environment and biota, and the toxicity of tyre particles and some of their chemical constituents, therefore, remain a major concern, which needs to be addressed by the global community. Exposure differences, health vulnerabilities and socio-economic factors are general gender-related aspects of microplastics pollution (UNEP 2023) and, where possible, should be taken into consideration when developing policies that aim at lowering the emissions of tyre particles.

What are the main findings?

Characteristics of tyre-wear particles

Tyre-wear particles deposited on or near a road typically range in size between a few micrometres (µm) and about 1500 µm, or 0.15 centimetres (Figure 5). They have an elongated shape and are partially covered by even smaller particles (Figure 6), derived primarily from the road surface but also from vehicle-brake pads and soils (Adachi and Tainosho 2004). Therefore, they are commonly referred to as *tyre- and road-wear particles* in the scientific literature (Baensch-Baltruschat *et al.* 2020). These particles occur most abundantly in road dust that accumulates in curves of roads and roundabouts and at traffic lights (Venghaus *et al.* 2023).



Photo credit: Photo by Jaydee Edwards

Figure 5: Tyre-wear particles viewed under a light microscope. Scale bar shows 500 micrometres.



Photo credit: Photo by Jaydee Edwards

Figure 6: Tyre-wear particle viewed under a scanning electron microscope, demonstrating that its surface is partially covered with small particles derived from vehicle brakes, the road surface, and local soils. Scale bar shows 100 micrometres.

Emission estimates

On average, passenger cars emit approximately 100 milligrams (mg) of tyre-wear particles per kilometre (km), implying that about 1 gram of tyre debris is released for every 10 km driven (Gieré and Dietze 2022). Emissions are considerably higher for heavier vehicles, such as vans, buses, and trucks (Figure 7), independent of the type of road travelled (Figure 8). On rural roads, however, all vehicle categories emit smaller amounts of tyre-wear particles than on urban roads (Figure 8).



Figure 7: Emissions of tyre-wear particles (in milligrams per kilometre for various types of vehicles. Data compiled from multiple sources (Gebbe *et al.* 1997; Gustafsson 2002; Luhana *et al.* 2004; Hillenbrand *et al.* 2005; United Nations Economic Commission for Europe (UNECE) 2013; Verschoor *et al.* 2016; Kole *et al.* 2017; Grigoratos *et al.* 2018; Allgemeiner Deutscher Automobil-Club (ADAC) 2019; Lee *et al.* 2020). Symbols: x = mean value; horizontal line = median. Abbreviations: LDV = light-duty vehicle; HDV = heavy-duty vehicle (for example, a truck).

Photo credit: iStock.com / Anna Bergbauer



Figure 8: Emissions of tyre-wear particles (in milligrams per kilometre) for various types of vehicles on rural roads, highways, and urban roads. Data compiled from Verschoor *et al.* (2016). Abbreviations: LDV = light-duty vehicle; HDV = heavy-duty vehicle.



Figure 9: Schematic diagram illustrating the transport of tyre-wear particles from the source to various environmental compartments, whereby road runoff represents the main pathway into soils, surface waters and sediments.

It is predicted that releases of vehicle tyre particles, along with those of other non-exhaust materials, such as brake-wear particles, will increase both in absolute terms and relative to the emissions from fuel combustion. This rise results from a continuing increase in traffic as well as from the growing number of electric vehicles in circulation, which – due to the battery weight – are generally heavier than similarly-sized vehicles with internal combustion engines and thus impart a considerably higher twisting force, known as torque, on the tyre tread (Amato *et al.* 2012; Timmers and Achten 2016; Jekel 2019; Organisation for Economic Co-operation and Development (OECD) 2020; Vanherle *et al.* 2021; Gehrke *et al.* 2023).

Release into the environment

Small amounts of tyre-wear particles are initially released directly into the atmosphere, whereas the majority first settles on the road surface (Baensch-Baltruschat *et al.* 2021). From these temporary sinks, they are then redistributed through wind or water and deposited in various environmental compartments (Figure 9) (Jekel 2019; Sieber *et al.* 2020; Cho *et al.* 2021; Prenner *et al.* 2021; Giechaskiel *et al.* 2024). Because road runoff in many settings is not collected by a sewer system and thus, not delivered to wastewater-treatment facilities, it plays a central role in transporting tyre-wear particles and associated pollutants to soils and surface waters (Maltby *et al.* 1995a; Maltby *et al.* 1995b; Boxall and Maltby 1997; Kumata *et al.* 2002; Sundt *et al.* 2016; Parker-Jurd *et al.* 2021; Chen *et al.* 2024).

Toxicity

During manufacturing of a tyre, various chemicals and fillers are added to the rubber polymers to enhance materials processability and to maximize performance and lifetime of the final product (Table 1, Figure 3). Yet, upon physical, chemical, and microbial degradation of tyre particles, some of these chemical components can be leached from the particles into the environment or into the intestines of organisms that have ingested the tyre debris (Spies *et al.* 1987; Reddy and Quinn 1997; Kumata *et al.* 2000; Johannessen *et al.* 2021). Recent studies have documented a hazardous potential of several leached tyre-derived chemicals (Cao *et al.* 2022; Gieré and Dietze 2022; Jiang *et al.* 2023; Roubeau Dumont *et al.*

2023). For example, zinc as well as organic chemical additives (Table 1), such as benzothiazole compounds (accelerators) and 6PPD (antioxidant and antiozonant) and/or their derivatives can cause acute and chronic toxicity to aquatic wildlife, including salmon (Capolupo *et al.* 2020; Honda and Suzuki 2020; Cuajungco *et al.* 2021; Tian *et al.* 2021; Brinkmann *et al.* 2022; Foldvik *et al.* 2022; Hussain *et al.* 2022; Page *et al.* 2022; Peng *et al.* 2022; Tian *et al.* 2022; Yang *et al.* 2022; Chen *et al.* 2023; Lo *et al.* 2023; Bohara *et al.* 2024).

Some of these problematic tyre-derived chemical additives and their transformation products have also been found in lettuce leaves, where they are metabolized and accumulated (Castan *et al.* 2023).

Tyre-wear particles that become airborne are typically smaller (less than 10 µm across) than those settling on the road surface (Giechaskiel *et al.* 2024), and thus are inhalable (Gustafsson *et al.* 2008). Because the smallest particles are produced through thermochemical processes rather than friction between tyres and road surface, this size fraction is chemically different as well. It consists primarily of carbon compounds and polymers (Dahl *et al.* 2006; Park *et al.* 2017; Johannessen *et al.* 2022; Chae *et al.* 2024), and thus has a different hazardous potential (Vallabani *et al.* 2023).

What has been done?

Measures to alleviate the problems of abundance and hazardous potential of tyre particles in the environment are focused on both prevention and mitigation (Piscitello *et al.* 2021; Gehrke *et al.* 2023).

Prevention

Prevention methods to minimize tyre-particle emissions at their source include: advanced design of tyre materials, such as modification of rubber into a self-healing material, capable of repairing damage and delaying tyre aging (Mandal *et al.* 2023a; Mandal *et al.* 2023b); innovation in developing new road pavements (Miera-Dominguez *et al.* 2023); optimizing the automotive axle systems (Schütte and Sextro 2021); investing in road maintenance to preserve a smooth surface (Gehrke *et al.* 2023); installing devices behind the wheels that capture tyre-wear particles (Dong *et al.* 2021); substituting problematic tyre components with more environmentally friendly chemicals to reduce the release of toxic compounds (Ayar *et al.* 2021; Börüban Bingöl *et al.* 2024); implementing stronger policies, which promote using public transport to reduce the number of vehicles on the road and stimulate transporting cargo by rail (Sundt *et al.* 2016); reducing traffic density and speed (Tian *et al.* 2017; Querol *et al.* 2018; Sommer *et al.* 2018); changing fleet composition to smaller and lighter vehicles (Andersson-Sköld *et al.* 2020); enhancing on-board driver-assistance and traffic-management systems to facilitate traffic flow with fewer brake maneuvers (Gieré and Dietze 2022); and consumer education on driving behavior, tyre choice, maintaining correct tyre-inflation pressure, vehicle maintenance (e.g., wheel alignment) and environmental impacts of driving (Fussell *et al.* 2022). The current efforts by the tyre industry to substitute some major components, such as carbon black and silica, with more sustainably-sourced materials (Lolage *et al.* 2020; Scott 2023) are a promising way forward, but the issue of the toxic chemical tyre additives must also be addressed, requiring swift action.

Mitigation

The transport of tyre-wear particles to locations far from the source of release can be reduced by various measures, including: applying porous asphalt to trap tyre particles on the road surface (Kole *et al.* 2017; Miera-Dominguez *et al.* 2023; Svensson *et al.* 2023); sweeping and rinsing of the road surface in high-traffic areas (Querol *et al.* 2018; Piscitello *et al.* 2021); spraying water or hygroscopic solutions onto the road surface to keep it moist, thus preventing resuspension and dispersion of road dust (Fussell *et al.* 2022; Gehrke *et al.* 2023); improving stormwater management to reduce road runoff into soils and surface waters by installing roadside settling ponds and gullies (Furuseth and Rødland 2020; Gehrke *et al.* 2023); connecting road-drainage systems to wastewater-treatment infrastructure while, at the same time, banning the use of the resulting sewage sludge as fertilizer (Gieré and Dietze 2022); and by planting suitable vegetation which, depending on geometrical features and surface roughness of the leaves, can trap tyre-wear particles along roadsides (Cho *et al.* 2021). Once the tyre-wear particles are in the soil or surface waters, it is almost impossible to recover them.

Photo credits iStock.com / Vladimir Razguliaev

Table 2: Roles of various stakeholders in addressing tyre-particle emissions and reducing the environmental impact of tyre manufacturing and usage

Stakeholder	Action
Governments (national, regional, and local)	• Invest in research on environmentally friendly tyre design • Policies to regulate tyre-particle emissions and to reduce the number of vehicle-kilometres travelled • Certain chemical components added during the tyre manufacturing process should be regulated or banned to reduce their documented toxic effects • Information related to chemical additives used for tyre manufacturing should be disclosed • Strong public policies must be developed and implemented to target non-exhaust traffic emissions
Businesses (e.g., tyre and car manufacturer, maintenance, service provider, recyclers)	• Advanced design of tyre materials, such as modification of rubber into a self-healing material, capable of repairing damage and delaying tyre aging • Substituting problematic tyre components with more environmentally friendly chemicals to reduce the release of toxic compounds • Substitute components, such as carbon black and silica, with more sustainably-sourced materials • Enhance on-board driver-assistance systems
Municipalities	• Invest in road maintenance to safeguard a smooth surface • Install traffic-management systems to facilitate traffic flow with fewer brake maneuvers • Direct road drainage to wastewater-treatment facilities
Consumers and users	• Reduce overall speed • Avoid rapid acceleration and braking • Drive with correctly inflated tyres • Use smaller and lighter vehicles • Choose public transport

What are the policy implications?

To reduce emission of tyre-wear particles and to minimize their dispersion into various environmental compartments, measures must be taken by a variety of stakeholders (Table 2), including tyre manufacturers, the automotive industry, road-construction companies, the wastewater sector, governments, research institutions, and environmental organizations, as well as educators and the media (European Tyre & Rubber Manufacturers Association (ETRMA) 2019; Gehrke *et al.* 2023). These stakeholders must be brought together in a joint effort to raise awareness in the society at large and to find suitable solutions to the ever-increasing accumulation of small tyre-wear particles in the environment and the associated release of hazardous chemicals during their degradation.

Unlike in the case of vehicle exhaust emissions, there are only a few policy instruments targeting non-exhaust traffic emissions. For example, in the European Union, various efforts exist to regulate tyre-particle emissions and to reduce the number of vehicle-kilometres travelled; measures include economic disincentives and/or potentially actual emission limits for heavier vehicles, as well as various incentives to increase the use of public transportation (OECD 2020). Elsewhere, the Road Traffic Regulations, issued by the government of Ghana, for example, prohibit the use of under- and overinflated tyres (Driver and Vehicle Licensing Agency (DVLA) 2012), which helps in reducing tyre-particle emissions (for example Fisher 2017).

On the material side, while essential tyre properties and safety requirements must be maintained, certain chemical components added during the tyre manufacturing process (e.g., 6PPD, PAHs, benzothiazoles) should be regulated or banned to reduce their documented toxic effects. An example of such a measure is a European Commission Regulation that has prohibited the placing on the market of extender oils or using them for the manufacturing of tyres or parts of tyres, if they contain certain PAHs in concentrations above a given limit (European Commission (EC) 2009). Elsewhere, new legislation implemented by California's Department of Toxic Substances Control (DTSC) 2023a, DTSC 2023b) mandates that tyre manufacturers search for alternatives to one of the main chemical additives of concern (6PPD). Similar initiatives should be pursued by governments around the world. In addition, effective policies must also be developed and implemented to improve transparency regarding the various chemicals used during tyre manufacturing (Trudsø *et al.* 2022).

In urban areas, road drainage systems should be connected to wastewater-treatment facilities, which have been documented to retain a major part of the tyre-wear particles (Baensch-Baltruschat *et al.* 2021; Parker-Jurd *et al.* 2021). The treatment of road runoff should also include procedures for the abatement of various organic chemicals contained in tyre-derived particles, and more generally, in road dust. Limited budgets or other priorities of policymakers (for example in low- and middle-income countries), however, may delay implementation of these recommendations, especially where the transport infrastructure is older.

Conclusions

Additional research as well as innovation and effective policies are urgently needed to lower the emissions of tyre-wear particles into the environment. Information related to chemical additives used for tyre manufacturing should be disclosed, and regulations should ensure the use of safer and more sustainable alternatives. Other important measures include improvement of traffic-management and road-drainage systems, strictly enforced regulations on speed limits, and enhanced driver education.

© 2024 United Nations Environment Programme

ISBN: 978-92-807-4177-3
Job Number: DEW/2665/NA

This publication may be reproduced in whole or in part and in any form for educational or non-profit services without special permission from the copyright holder, provided acknowledgement of the source is made. The United Nations Environment Programme would appreciate receiving a copy of any publication that uses this publication as a source.

No use of this publication may be made for resale or any other commercial purpose whatsoever without prior permission in writing from the Secretariat of the United Nations. Applications for such permission, with a statement of the purpose and extent of the reproduction, should be addressed to the Director, Communication Division, United Nations Environment Programme, unep-communication-director@un.org.

Disclaimers

The designations employed and the presentation of the material in this publication do not imply the expression of any opinion whatsoever on the part of the Secretariat of the United Nations concerning the legal status of any country, territory or city or area or of its authorities, or concerning the delimitation of its frontiers or boundaries.

Some illustrations or graphics appearing in this publication may have been adapted from content published by third parties to illustrate the authors' own interpretations of the key messages emerging from such third-party illustrations or graphics. In such cases, the material in this publication does not imply the expression of any opinion whatsoever on the part of United Nations Environment Programme concerning the source materials used as a basis for such graphics or illustrations.

Mention of a commercial company or product in this document does not imply endorsement by the United Nations Environment Programme or the authors. The use of information from this document for publicity or advertising is not permitted. Trademark names and symbols are used in an editorial fashion with no intention on infringement of trademark or copyright laws.

The views expressed in this publication are those of the authors and do not necessarily reflect the views of the United Nations Environment Programme. We regret any errors or omissions that may have been unwittingly made.

© Maps, photos and illustrations as specified

Suggested citation

United Nations Environment Programme (2024). *Vehicle tyre particles in the environment - Foresight Brief 034*
URL - https://wedocs.unep.org/20.500.11822/46239
DOI - https://doi.org/10.59117/20.500.11822/46239

Authors

Reto Gieré, University of Pennsylvania, Philadelphia, USA
Jaydee Edwards, University of Pennsylvania, Philadelphia, USA
Volker Dietze, German Meteorological Service, Freiburg, Germany
Radek Stoček, Polymer Research Lab and Tomáš Bata University, Zlín, Zlín, Czech Republic
Gert Heinrich, Dresden University of Technology, Dresden, Germany

Acknowledgements

Reviewers

UNEP Reviewers

Feng Wang, Claudia Giacovelli, Stephanie Laruelle, Felipe Dall and Markos Ieridis, Raymond Brandes, Bavelyne Mibei, Carly Koinange, Pinya Sarasas, Angeline Djampou, Jane Muriithi, Samuel Opiyo

External Reviewers

Karen Raubenheimer, Senior Lecturer, ANCORS, Faculty of Business and Law, University of Wollongong, New South Wales, Australia

Mary Ellen Ternes, Senior Fellow, Law and Policy, Global Council for Science and the Environment

Hideshige Takada, Ph.D, Professor, Laboratory of Organic Geochemistry (LOG), Tokyo University of Agriculture and Technology, Fuchu, Tokyo, Japan

Prof. Marian Asantewah Nkansah (PhD, MRSC, – FGA), Associate Professor, Department of Chemistry, Kwame Nkrumah University of Science and Technology, (KNUST), Kumasi, Ghana

Editor

Alison Bullen

Foresight Brief Team

Alexandre Caldas, Sandor Frigyik, Audrey Ringler, Esther Katu, Erick Litswa, Pascil Muchesia

Production

System Analysis and Foresight Briefs Unit, Big Data Branch, Early Warning and Assessment Division, UNEP

Contact

unep-foresight@un.org

Bibliography

Aatmeeyata, and Sharma, M. (2010). Polycyclic aromatic hydrocarbons, elemental and organic carbon emissions from tire-wear. *Science of the Total Environment* 408(20), 4563–4568. https://doi.org/10.1016/j.scitotenv.2010.06.011

Adachi, K. and Tainosho, Y. (2004). Characterization of heavy metal particles embedded in tire dust, *Environment International* 30(8), 1009–1017. https://doi.org/10.1016/j.envint.2004.04.004

Allgemeiner Deutscher Automobil-Club (ADAC) (2019). *Verschleiss und Reifenabrieb (Tire wear and abrasion)*. Cited in Prenner *et al.* 2021: Allgemeiner Deutscher Automobil-Club (ADAC), available upon personal request (in German). *https://assets.adac.de/image/upload/v1639663105/ADAC-eV/KOR/Text/PDF/Tyre_wear_particles_in_the_environment_zkmd3a.pdf*

Amato, F., Karanasiou, A., Moreno, T., Alastuey, A., Orza, J.A.G., Lumbreras, J., *et al.* (2012). Emission factors from road dust resuspension in a Mediterranean freeway. *Atmospheric Environment* 61, 580–587. https://doi.org/10.1016/j.atmosenv.2012.07.065

Andersson-Sköld, Y., Johannesson, M., Gustafsson, M., Järlskog, I., Lithner, D., Polukarova, M. *et al.* (2020). Microplastics from tyre and road wear: a literature review. https://doi.10.13140/RG.2.2.34478.54083

Ayar, M., Dalkiran, A., Kale, U., Nagy, A., and Karakoc, T.H. (2021). Investigation of the Substitutability of Rubber Compounds with Environmentally Friendly Materials. *Sustainability* 13(9), 5251. https://doi.org/10.3390/su13095251

Baensch-Baltruschat, B., Kocher, B., Kochleus, C., Stock, F. and Reifferscheid, G. (2021). Tyre and road wear particles - A calculation of generation, transport and release to water and soil with special regard to German roads. *Science of the Total Environment* 752, 141939. https://doi.org/10.1016/j.scitotenv.2020.141939

Baensch-Baltruschat, B., Kocher, B., Stock, F., and Reifferscheid, G. (2020). Tyre and road wear particles (TRWP) - A review of generation, properties, emissions, human health risk, ecotoxicity, and fate in the environment. *Science of the Total Environment* 733, 137823. https://doi.org/10.1016/j.scitotenv.2020.137823

Bohara, K., Timilsina, A., Adhikari, K., Kafle, A., Basyal, S., Joshi, P. *et al.* (2024). A mini review on 6PPD quinone: A new threat to aquaculture and fisheries, *Environmental Pollution* 340, 122828. https://doi.org/10.1016/j.envpol.2023.122828

Boonyatumanond, R., Murakami, M., Wattayakorn, G., Togo, A. and Takada, H. (2007). Sources of polycyclic aromatic hydrocarbons (PAHs) in street dust in a tropical Asian mega-city, Bangkok, Thailand. *Science of the Total Environment*, 384(1), 420–432. https://doi.org/10.1016/j.scitotenv.2007.06.046

Börühan, B., Ningöl, C., Polat, S. and Atapek, Ş.H. (2024). Wear Behavior of SBR/BR Compounds Including Different ZnO Types. *Journal of Physics: Conference Series* 2692(1), 012010. https://doi.org/10.1088/1742-6596/2692/1/012010

Boucher, J. and Friot, D. (2017). *Primary microplastics in the oceans: a global evaluation of sources*. Gland, Switzerland: International Union for Conservation of Nature (IUCN). https://doi.org/10.2305/iucn.ch.2017.01.en

Boxall, A.B.A., and Maltby, L. (1997). The effects of motorway runoff on freshwater ecosystems: 3. Toxicant confirmation. *Archives of Environmental Contamination and Toxicology*, 33, 9–16. https://doi.org/10.1007/s002449900216

Brinkmann, M., Montgomery, D., Selinger, S., Miller, J.G.P., Stock, E., Alcaraz, A.J., *et al.* (2022). Acute Toxicity of the Tire Rubber-Derived Chemical 6PPD-quinone to Four Fishes of Commercial, Cultural, and Ecological Importance. *Environmental Science & Technology Letters* 9(4), 333–338. https://doi.org/10.1021/acs.estlett.2c00050

Broekhuizen, P. (2024). *Airborne release of tyre wear particles - update 2024*. https://doi.org/10.13140/RG.2.2.19335.57760

Cao, G., Wang, W., Zhang, J., Wu, P., Zhao, X., Yang, Z., *et al.* (2022). New Evidence of Rubber-Derived Quinones in Water, Air, and Soil. *Environmental Science & Technology* 56(7), 4142–4150. https://doi.org/10.1021/acs.est.1c07376

Capolupo, M., Sørensen, L., Jayasena, K.D.R., Booth, A.M., and Fabbri, E. (2020). Chemical composition and ecotoxicity of plastic and car tire rubber leachates to aquatic organisms. *Water Research* 169, 115270. https://doi.org/10.1016/j.watres.2019.115270

Castan, S., Sherman, A., Peng, R., Zumstein, M. T., Wanek, W., Hüffer, T. and Hofmann, T. (2023). Uptake, Metabolism, and Accumulation of Tire Wear Particle-Derived Compounds in Lettuce. *Environmental Science & Technology* 57(1), 168–178. https://doi.org/10.1021/acs.est.2c05660

Chae, E., Jung, U. and Choi, S.S. (2024) Seasonal variations in concentrations of PM2.5 and tire wear particle of < 2.5 μm (TWP2.5) and polymeric components of PM2.5 at a bus stop. *Atmospheric Environment* 318, 120243. https://doi.org/10.1016/j.atmosenv.2023.120243

Chen, J., Tang, T., Li, Y., Wang, R., Chen, X., Song, D., *et al.* (2024). Non-targeted screening and photolysis transformation of tire-related compounds in roadway runoff. *Science of the Total Environment* 924, 171622. https://doi.org/10.1016/j.scitotenv.2024.171622

Chen, X., Ye, T., Yang, X., Gan, Y., Qing, X., Wang, J. and Huang, Y. (2023). Analysis, environmental occurrence, fate and potential toxicity of tire wear compounds 6PPD and 6PPD-quinone. *Journal of Hazardous Materials* 452, 131245. https://doi.org/10.1016/j.jhazmat.2023.131245

Cho, M.-C., Jo, Y.-G., Son, J.A., Kim, I., Oh, C. and Yook, S.-J. (2021). Deposition characteristics of soot and tire-wear particles on urban tree leaves. *Journal of Aerosol Science* 155, 105768. https://doi.org/10.1016/j.jaerosci.2021.105768

Cuajungco, M., Ramirez, M. and Tolmasky, M. (2021). Zinc: Multidimensional Effects on Living Organisms, *Biomedicines* 9(2), 208. https://doi.org/10.3390/biomedicines9020208

Dahl, A., Gharibi, A., Swietlicki, E., Gudmundsson, A., Bohgard, M., Ljungman, A., *et al.* (2006). Traffic-generated emissions of ultrafine particles from pavement-tire interface. *Atmospheric Environment* 40(7), 1314. https://doi.org/10.1016/j.atmosenv.2005.10.029

Dong, J., Huang, H., Pei, J., Xu, Y. and Cao, J. (2021). A methodology for capturing tire wear particles: Computational particle fluid dynamics modelling and experimental verification, *Powder Technology* 384, 176–185. https://doi.org/10.1016/j.powtec.2021.02.016

Department of Toxic Substances Control (DTSC) (2023a). Adopted priority product: motor vehicle tires containing 6PPD. https://dtsc.ca.gov/scp/motor_vehicle_tires_containing_6ppd

Department of Toxic Substances Control (DTSC) (2023b). California requires tiremakers to look for safer alternatives to chemical that kills Coho salmon. https://dtsc.ca.gov/2023/07/26/news-release_t-06-23/

Driver and Vehicle Licensing Agency (DVLA) (2012). The Road Traffic Regulations, L.I. 2180. Driver and Vehicle Licensing Authority, Government of Ghana. https://www.dvla.gov.gh/singlenews

European Commission (EC) (2009). *Commission Regulation (EC) No 552/2009; https://eur-lex.europa.eu/LexUriServ/LexUriServ.do?uri=OJ:L:2009:164:0007:0031:EN:PDF*. The Commission of the European Communities.

European Tyre & Rubber Manufacturers Association (ETRMA) (2019). European TRWP Platform: Way Forward Report. *https://www.etrma.org/wp-content/uploads/2019/10/20200330-FINAL-Way-Forward-Report.pdf*

Evans, J.J. (1997). Rubber Tire Leachates in the Aquatic Environment, *Reviews of Environmental Contamination and Toxicology*, 67–115. https://doi.org/10.1007/978-1-4612-1958-3_3

Fisher, P. (2017). Effects of improper inflation pressure on treadwear. *Tire Business*. https://www.tirebusiness.com/article/20170922/NEWS/170929981/effects-of-improper-inflation-pressure-on-treadwear

Foldvik, A., Kryuchkov, F., Sandodden, R. and Uhlig, S. (2022). Acute Toxicity Testing of the Tire Rubber–Derived Chemical 6PPD-quinone on Atlantic Salmon (Salmo salar) and Brown Trout (Salmo trutta). *Environmental Toxicology and Chemistry* 41(12), 3041–3045. https://doi.org/10.1002/etc.5487

Furuseth, S. and Rødland, S. (2020). *Reducing the release of microplastics from tire wear: Nordic efforts. Report NA2020-909, ISSN 2311-0562*. Norwegian Institute of Water Research. https://doi.org/10.6027/na2020-909

Fussell, J.C., Franklin, M., Green, D.C., Gustafsson, M., Harrison, R. M., Hicks, W., *et al.* (2022). A Review of Road Traffic-Derived Non-Exhaust Particles: Emissions, Physicochemical Characteristics, Health Risks, and Mitigation Measures. *Environmental Science & Technology* 56(11), 6813–6835. https://doi.org/10.1021/acs.est.2c01072

Gebbe, M., Hartung, J. and Berthold, O. (1997). *Quantifizierung des Reifenabriebs von Kraftfahrzeugen in Berlin, Teil II: Endbericht*. TU Berlin, ISS-Fahrzeugtechnik, im Auftrag der Senatsverwaltung für Stadtentwicklung, Umweltschutz und Technologie, Berlin; pp.77. *https://www.luft.sachsen.de/download/luft/Abschlussbericht_Aufwirblung_Abrieb.pdf*

Gehrke, I., Schläfle, S., Bertling, R., Öz, M. and Gregory, K. (2023). Review: Mitigation measures to reduce tire and road wear particles. *Science of the Total Environment* 904, 166537. https://doi.org/10.1016/j.scitotenv.2023.166537

Gent, A.N. (2006). Mechanical properties of rubber. In A. N. Gent and W. J.D. (Eds.), *The pneumatic tire* (pp. 29–77, *https://www.nhtsa.gov/sites/nhtsa.gov/files/pneumatictire_hs-810-561.pdf*): U.S. Department of Transportation, National Highway Traffic Safety Administration.

Giechaskiel, B., Grigoratos, T., Mathissen, M., Quik, J., Tromp, P., Gustafsson, M., *et al.* (2024). Contribution of Road Vehicle Tyre Wear to Microplastics and Ambient Air Pollution, *Sustainability*, 16(2), 522. https://doi.org/10.3390/su16020522

Gieré, R., and Dietze, V. (2022). Tire-abrasion particles in the environment. In G. Heinrich, R. Kipscholl, & R. Stoček (Eds.), *Degradation of elastomers in practice, experiments and modeling* (Vol. Advances in Polymer Science 289, pp. 71–102). Cham, Switzerland: Springer. https://doi.org/10.1007/122_2022_118

Gieré, R., LaFree, S.T., Carleton, L.E. and Tishmack, J.K. (2004). Environmental impact of energy recovery from waste tyres. In R. Gieré and P. Stille (Eds.), *Energy, Waste, and the Environment: a Geochemical Perspective* 236, 475–498. The Geological Society, London. https://doi.org/10.1144/gsl.sp.2004.236.01.26

Grigoratos, T., Gustafsson, M., Eriksson, O. and Martini, G. (2018). Experimental investigation of tread wear and particle emission from tyres with different treadwear marking. *Atmospheric Environment* 182, 200–212. https://doi.org/10.1016/j.atmosenv.2018.03.049

Gustafsson, M. (2002). *Non-exhaust particles in the road environment: A literature review*. Paper presented at the PIARC 2002 Xth International Winter Road Congress 28–31 January 2002 -Sapporo (Japan). https://doi.org/10.1016/j.scitotenv.2022.156950

Gustafsson, M., Blomqvist, G., Gudmundsson, A., Dahl, A., Swietlicki, E., Bohgard, M., *et al.* (2008). Properties and toxicological effects of particles from the interaction between tyres, road pavement and winter traction material, *The Science of the Total Environment*, 393(2), 226–240. https://doi.org/10.1016/j.scitotenv.2007.12.030

Halle, L.L., Palmqvist, A., Kampmann, K. and Khan, F.R. (2020). Ecotoxicology of micronized tire rubber: Past, present and future considerations. *Science of the Total Environment 706*, 135694. https://doi.org/10.1016/j.scitotenv.2019.135694

Halsband, C., Sørensen, L., Booth, A.M. and Herzke, D. (2020). Car Tire Crumb Rubber: Does Leaching Produce a Toxic Chemical Cocktail in Coastal Marine Systems? *Frontiers in Environmental Science* 8(125). https://doi.org/10.3389/fenvs.2020.00125

Hartmann, N.B., Hüffer, T., Thompson, R.C., Hassellöv, M., Verschoor, A., Daugaard, A.E., *et al.* (2019). Are We Speaking the Same Language? Recommendations for a Definition and Categorization Framework for Plastic Debris, *Environmental Science & Technology* 53(3), 1039–1047. https://doi.org/10.1021/acs.est.8b05297

Hillenbrand, T., Toussaint, D., Böhm, E., Fuchs, S., Scherer, U., Rudolphi, A., and Hoffmann, M. (2005). *Einträge von Kupfer, Zink und Blei in Gewässer und Böden - Analyse der Emissionspfade und möglicher Emissionsminderungsmaßnahmen. UBA-Texte 19/05. https://www.umweltbundesamt.de/sites/default/files/medien/publikation/long/2936.pdf*. Dessau, Germany: Umweltbundesamt.

Honda, M. and Suzuki, N. (2020). Toxicities of Polycyclic Aromatic Hydrocarbons for Aquatic Animals, *International Journal of Environmental Research and Public Health* 17(4), 1363. https://doi.org/10.3390/ijerph17041363

Hussain, S., Khan, M., Sheikh, T.M.M., Mumtaz, M.Z., Chohan, T.A., Shamim, S. and Liu, Y. (2022). Zinc Essentiality, Toxicity, and Its Bacterial Bioremediation: A Comprehensive Insight. *Frontiers in Microbiology* 13. Review. https://doi.org/10.3389/fmicb.2022.1133733

Järskog, I., Jaramillo-Vogel, D., Rausa, M., Gustafsson. M., Strömvall, A.-M., Andersson-Sköld, Y. (2022). Concentrations of tire wear microplastics and other traffic-derived non-exhaust particles in the road environment. *Environment International* 170, 107618. https://doi.org/10.1016/j.envint.2022.107618

Jekel, M. (2019). *Scientific report on tyre and road wear Particles, TRWP, in the aquatic environment. https://www.tyreandroadwear.com/wp-content/uploads/2019/10/FINAL-Scientific-Report-on-Tyre-and-Road-Wear-Particles.pdf*. Brussels: European Tyre & Rubber Manufacturers Association (ETMRA).

Jiang, J.-R., Chen, Z.-F., Liao, X.-L., Liu, Q.-Y., Zhou, J.-M., Ou, S.-P. and Cai, Z. (2023). Identifying potential toxic organic substances in leachates from tire wear particles and their mechanisms of toxicity to Scenedesmus obliquus. *Journal of Hazardous Materials* 458, 132022. https://doi.org/10.1016/j.jhazmat.2023.132022

Johannessen, C., Helm, P. and Metcalfe, C.D. (2021). Detection of selected tire wear compounds in urban receiving waters, *Environmental Pollution*, 287, 117659. https://doi.org/10.1016/j.envpol.2021.117659

Johannessen, C., Liggio, J., Zhang, X., Saini, A. and Harner, T. (2022). Composition and transformation chemistry of tire-wear derived organic chemicals and implications for air pollution. *Atmospheric Pollution Research*, 13(9), 101533. https://doi.org/10.1016/j.apr.2022.101533

Kole, P.J., Löhr, A.J., Van Belleghem, F.G.A.J. and Ragas, A.M.J. (2017). Wear and Tear of Tyres: A Stealthy Source of Microplastics in the Environment. *International Journal of Environmental Research and Public Health*, 14(10). https://doi.org/10.3390/ijerph14101265

Kole, P.J., Löhr, A.J., Van Belleghem, F.G.A.J. and Ragas, A.M.J. (2019). *Wear and tear of tyres in the global environment: size distribution, emissions, pathways and health effects*. Paper presented at the SETAC Europe 29th Annual Meeting, Helsinki. https://www.researchgate.net/publication/332523507

Kumata, H., Sanada, Y., Takada, H., and Ueno, T. (2000). Historical Trends of N-Cyclohexyl-2-benzothiazolamine, 2-(4-Morpholinyl) benzothiazole, and Other Anthropogenic Contaminants in the Urban Reservoir Sediment Core. *Environmental Science & Technology*, 34(2), 246–253. https://doi.org/10.1021/es990738k

Kumata, H., Yamada, J., Masuda, K., Takada, H., Sato, Y., Sakurai, T. and Fujiwara, K. (2002). Benzothiazolamines as Tire-Derived Molecular Markers: Sorptive Behavior in Street Runoff and Application to Source Apportioning. *Environmental Science & Technology* 36(4), 702–708. https://doi.org/10.1021/es0155229

Leads, R.R., Burnett, K.G. and Weinstein, J.E. (2019). The Effect of Microplastic Ingestion on Survival of the Grass Shrimp Palaemonetes pugio (Holthuis, 1949) Challenged with Vibrio campbellii, *Environmental Toxicology and Chemistry* 38(10), 2233–2242. https://doi.org/10.1002/etc.4545

Lee, H., Ju, M. and Kim, Y. (2020). Estimation of emission of tire wear particles (TWPs) in Korea, *Waste Management* 108, 154–159. https://doi.org/10.1016/j.wasman.2020.04.037

Liao, C., Kim, U.-J. and Kannan, K. (2018). A Review of Environmental Occurrence, Fate, Exposure, and Toxicity of Benzothiazoles, *Environmental Science & Technology* 52(9), 5007–5026. https://doi.org/10.1021/acs.est.7b05493

Lo, B.P., Marlatt, V.L., Liao, X., Reger, S., Gallilee, C., Ross, A.R.S. and Brown, T.M. (2023). Acute Toxicity of 6PPD-Quinone to Early Life Stage Juvenile Chinook (Oncorhynchus tshawytscha) and Coho (Oncorhynchus kisutch) Salmon. *Environmental Toxicology and Chemistry* 42(4), 815–822. https://doi.org/10.1002/etc.5568

Lolage, M., Parida, P., Chaskar, M., Gupta, A. and Rautaray, D. (2020). Green Silica: Industrially scalable & sustainable approach towards achieving improved mechanical properties of Nitrile Rubber – Elastomer interactions and reinforcement in tire tread compounds. *Sustainable Materials and Technologies* 26, e00232. https://doi.org/10.1016/j.susmat.2020.e00232

Lu, F., Su, Y., Ji, Y. and Ji, R. (2021). Release of Zinc and Polycyclic Aromatic Hydrocarbons From Tire Crumb Rubber and Toxicity of Leachate to Daphnia magna: Effects of Tire Source and Photoaging, *Bulletin of Environmental Contamination and Toxicology* 107(4), 651–656. https://doi.org/10.1007/s00128-021-03123-9

Luhana, L., Sokhi, R., Warner, L., Mao, H., Boulter P., McCrae, I., *et al.* (2004). *Measurement of non-exhaust particulate matter. Version 2.0. PARTICULATES – Characterisation of exhaust particulate emissions from road vehicles. Deliverable 8*.: European Commission, Directorate General Transport and Environment. https://www.researchgate.net/publication/303018119_Measurement_of_non-exhaust_particulate_matter

Maltby, L., Boxall, A.B.A., Forrow, D.M., Calow, P. and Betton, C.I. (1995a). The effects of motorway runoff on freshwater ecosystems: 2. Identifying major toxicants. *Environmental Toxicology and Chemistry*, 14(6), 1093–1101. https://doi.org/10.1002/etc.5620140621

Maltby, L., Forrow, D.M., Boxall, A.B.A., Calow, P. and Betton, C.I. (1995b). The effects of motorway runoff on freshwater ecosystems: 1. Field study. *Environmental Toxicology and Chemistry* 14(6), 1079–1092. https://doi.org/10.1002/etc.5620140620

Mandal, S., Das, A., Euchler, E., Wiessner, S., Heinrich, G., Sawada, J., *et al.* (2023a). Dynamic Reversible Networks and Development of Self-Healing Rubbers: A Critical Review. *Rubber Chemistry and Technology*, 96(2), 175–195. https://doi.org/10.5254/rct.23.76967

Mandal, S., Malanin, M., Ghanti, B., Banerjee, S., Sawada, J., Tada, T., *et al.* (2023b). Design of sacrificial network in modified natural rubber leads to strikingly improved mechanical performance with self-healing capability. *Chemical Engineering Journal* 474, 145838. https://doi.org/10.1016/j.cej.2023.145838

Miera-Domínguez, H., Indacoechea-Vega, I., Lastra-González, P., van Loon, R., van Blokland, G. and Castro-Fresno, D. (2023). Low-noise and pollutant-reducing asphalt mixtures. *Transportation Research Procedi, 72*, 3308–3315. https://doi.org/10.1016/j.trpro.2023.11.796

Müller, K., Hübner, D., Huppertsberg, S., Knepper, T.P. and Zahn, D. (2022). Probing the chemical complexity of tires: Identification of potential tire-borne water contaminants with high-resolution mass spectrometry. *Science of the Total Environment*, 802, 149799. https://doi.org/10.1016/j.scitotenv.2021.149799

Organisation for Economic Co-operation and Development (OECD) (2014). *Nanotechnology and Tyres* (2014) *OECD eBooks*. https://doi.org/10.1787/9789264209152-en. Paris, France: OECD Publishing Retrieved from https://www.oecd-ilibrary.org/content/publication/9789264209152-en

Organisation for Economic Co-operation and Development (OECD) (2020). *Non-exhaust Particulate Emissions from Road Transport: An Ignored Environmental Policy Challenge*. OECD Publishing, Paris. https://doi.org/10.1787/4a4dcbca-en

Page, T.S., Almeda, R., Koski, M., Bournaka, E. and Nielsen, T.G. (2022). Toxicity of tyre wear particle leachates to marine phytoplankton, *Aquatic Toxicology* 252, 106299. https://doi.org/10.1016/j.aquatox.2022.106299

Park, I., Lee, J. and Lee, S. (2017). Laboratory study of the generation of nanoparticles from tire tread, *Aerosol Science and Technology* 51(2), 188–197. https://doi.org/10.1080/02786826.2016.1248757

Parker, B.W., Beckingham, B.A., Ingram, B.C., Ballenger, J.C., Weinstein, J.E. and Sancho, G. (2020). Microplastic and tire wear particle occurrence in fishes from an urban estuary: Influence of feeding characteristics on exposure risk. *Marine Pollution Bulletin* 160, 111539. https://doi.org/10.1016/j.marpolbul.2020.111539

Parker-Jurd, F.N.F., Napper, I. E., Abbott, G.D., Hann, S. and Thompson, R.C. (2021). Quantifying the release of tyre wear particles to the marine environment via multiple pathways. *Marine Pollution Bulletin* 172, 112897. https://doi.org/10.1016/j.marpolbul.2021.112897

Peng, W., Liu, C., Chen, D., Duan, X. and Zhong, L. (2022). Exposure to N-(1,3-dimethylbutyl)-N′-phenyl-p-phenylenediamine (6PPD) affects the growth and development of zebrafish embryos/larvae. *Ecotoxicology and Environmental Safety* 232, 113221. https://doi.org/10.1016/j.ecoenv.2022.113221

Pew Charitable Trusts. (2020). *Breaking the plastic wave: a comprehensive assessment of pathways towards stopping ocean plastic pollution. https://www.pewtrusts.org/-/media/assets/2020/07/breakingtheplasticwave_report.pdf*

Piscitello, A., Bianco, C., Casasso, A. and Sethi, R. (2021). Non-exhaust traffic emissions: Sources, characterization, and mitigation measures. *Science of the Total Environment* 766, 144440. https://doi.org/10.1016/j.scitotenv.2020.144440

Prenner, S., Allesch, A., Staudner, M., Rexeis, M., Schwingshackl, M., Huber-Humer, M. and Part, F. (2021). Static modelling of the material flows of micro- and nanoplastic particles caused by the use of vehicle tyres. *Environmental Pollution* 290, 118102. https://doi.org/10.1016/j.envpol.2021.118102

Querol, X., Amato, F., Robusté, F., Holman, C. and Harrison, R.M. (2018). Chapter 11 - Non-technological Measures on Road Traffic to Abate Urban Air Pollution. In F. Amato (Ed.), *Non-Exhaust Emissions*, 229-260: Academic Press. https://doi.org/10.1016/b978-0-12-811770-5.00011-x

Rauert, C., Redland, E.S., Okoffo, E.D., Reid, M.J., Meland, S. and Thomas, K.V. (2021). Challenges with Quantifying Tire Road Wear Particles: Recognizing the Need for Further Refinement of the ISO Technical Specification. *Environmental Science & Technology Letters* 8(3), 231–236. https://doi.org/10.1021/acs.estlett.0c00949

Reddy, C.M., and Quinn, J.G. (1997). Environmental Chemistry of Benzothiazoles Derived from Rubber. *Environmental Science & Technology*, 31(10), 2847–2853. https://doi.org/10.1021/es970078o

Roubeau Dumont, E., Gao, X., Zhang, J., Hernandez, L.M., Baesu, A. *et al.* (2023). Unraveling the toxicity of tire wear contamination in three freshwater species: From chemical mixture to nanoparticles. *Journal of Hazardous Materials* 453, 131402. https://doi.org/10.1016/j.jhazmat.2023.131402

Schütte, J. and Sextro, W. (2021). Tire Wear Reduction Based on an Extended Multibody Rear Axle Model, *Vehicles*, 3(2), 233–256. https://doi.org/10.3390/vehicles3020015

Scott, N.A. (2023). Can tires turn green?, *C&EN Global Enterprise* 101(17), pp. 28–34. https://doi.org/10.1021/cen-10117-cover

Sieber, R., Kawecki, D. and Nowack, B. (2020). Dynamic probabilistic material flow analysis of rubber release from tires into the environment, *Environmental Pollution*, 258, 113573. https://doi.org/10.1016/j.envpol.2019.113573

Sommer, F., Dietze, V., Baum, A., Sauer, J., Gilge, S., Maschowski, C. and Gieré, R. (2018). Tire Abrasion as a Major Source of Microplastics in the Environment. *Aerosol and Air Quality Research* 18(8), 2014–2028. https://www.researchgate.net/publication/326063101_Tire_Abrasion_as_a_Major_Source_of_Microplastics_in_the_Environment

Spies, R.B., Andresen, B.D., and Rice Jr, D.W. (1987). Benzthiazoles in estuarine sediments as indicators of street runoff. *Nature*, 327(6124), 697-699. https://doi.org/10.1038/327697a0

Sundt, P., Syversen, F., Skogesal, O. and Schulze, P.-E. (2016). *Primary microplastic pollution: Measures and reduction potentials in Norway. https://www.miljodirektoratet.no/globalassets/publikasjoner/M545/M545.pdf*. Asker, Norway: Mepex Consult, for the Norwegian Environment Agency.

Svensson, N., Lundberg, J., Lunhäll, S., Kulovuori, S. and Gustafsson, M. (2023). Effects of a porous asphalt pavement on dust suspension and PM10 concentration. *Transportation Research Part D: Transport and Environment* 123, 103921. https://doi.org/10.1016/j.trd.2023.103921

Tian, Z., Dietze, V., Sommer, F., Baum, A., Kaminski, U., Sauer, J., *et al.* (2017). Coarse-Particle Passive-Sampler Measurements and Single-Particle Analysis by Transmitted Light Microscopy at Highly Frequented Motorways. *Aerosol and Air Quality Research*, 17(8), 1939–1952. https://doi.org/10.4209/aaqr.2017.02.0064

Tian, Z., Gonzalez, M., Rideout, C. A., Zhao, H.N., Hu, X., Wetzel, J., *et al.* (2022). 6PPD-Quinone: Revised Toxicity Assessment and Quantification with a Commercial Standard. *Environmental Science & Technology Letters* 9(2), 140–146. https://doi.org/10.1021/acs.estlett.1c00910

Tian, Z., Zhao, H., Peter, K.T., Gonzalez, M., Wetzel, J., Wu, C., *et al.* (2021). A ubiquitous tire rubber-derived chemical induces acute mortality in coho salmon. *Science* 371(6525), 185–189. https://doi.org/10.1126/science.abd6951

Timmers, V.R.J.H. and Achten, P.A.J. (2016). Non-exhaust PM emissions from electric vehicles, *Atmospheric Environment* 134, 10–17. https://doi.org/10.1016/j.atmosenv.2016.03.017

Trudsø, L.L., Nielsen, M.B., Hansen, S.F., Syberg, K., Kampmann, K., Khan, F.R., and Palmqvist, A. (2022). The need for environmental regulation of tires: Challenges and recommendations. *Environmental Pollution* 311, 119974. https://doi.org/10.1016/j.envpol.2022.119974

United Nations Economic Commission for Europe (UNECE) (2013). *Particulate Matter Emissions by Tyres. Informal Document GRPE-65-20, transmitted by the Expert from the Russian Federation; https://unece.org/DAM/trans/doc/2013/wp29grpe/GRPE-65-20e.pdf*. Geneva, Switzerland: United Nations Economic Commission for Europe, Working Party on Pollution and Energy (GRPE).

United Nations Environment Programme (UNEP) (2023). *Plastics in the environment in the context of UV radiation, climate change and the Montreal Protocol*. 2023 Assessment Update of the UNEP Environmental Effects Assessment Panel, UNEP: Nairobi, 2023.

Vallabani, N.V.S., Gruzieva, O., Elihn, K., Juárez-Facio, A.T., Steimer, S.S., Kuhn, J., *et al.* (2023). Toxicity and health effects of ultrafine particles: Towards an understanding of the relative impacts of different transport modes, *Environmental Research* 231, 116186. https://doi.org/10.1016/j.envres.2023.116186

Vanherle, K., Lopez-Aparicio, S., Grythe, H., Lükewille, A., Unterstaller, A. and Mayeres, I. (2021). *Transport non-exhaust PM emissions. Eionet Report ETC/ATNI 2020/5*. European Topic Centre on Air pollution, Transport, Noise and Industrial pollution, European Environment Agency. *https://www.eionet.europa.eu/etcs/etc-atni/products/etc-atni-reports/etc-atni-report-5-2020-transport-non-exhaust-pm-emissions-an-overview-of-emission-estimates-relevance-trends-and-policies/@@download/file/ETC-ATNI%202020-5_AP2020-task%201-3-9-4_201221_v10%20-%2002-03-2021%20FINAL.pdf*

Venghaus, D. Neuperl, J.W. and Barjenbruch, M. (2023). Tire Wear Monitoring Approach for Hotspot Identification in Road Deposited Sediments from a Metropolitan City in Germany, *Sustainability* 15(15), 12029. https://doi.org/10.3390/su151512029

Verschoor, A., de Poorter, L., Dröge, R., Kuenen, J. and de Valk, E. (2016). *Emission of microplastics and potential mitigation measures. RIVM Report 2016-0026. https://www.rivm.nl/bibliotheek/rapporten/2016-0026.html*. Bilthoven, The Netherlands: National Institute for Public Health and the Environment.

Vogelsang, C., Lusher, A.M., Dadkhah, M.E., Sundvor, I., Umar, M., Ranneklev, S.B., *et al.* (2020). *Microplastics in road dust - characteristics, pathways and measures. Report SNO. 7526-2020*. Oslo: Norwegian Institute for Water Research. https://www.researchgate.net/publication/324247730

Wagner, S., Hüffer, T., Klöckner, P., Wehrhahn, M., Hofmann, T. and Reemtsma, T. (2018). Tire wear particles in the aquatic environment - A review on generation, analysis, occurrence, fate and effects. *Water Research* 139, 83-100. https://doi.org/10.1016/j.watres.2018.03.051

Wan, L., Deng, C., Zhao, Z.-Y., Chen, H. and Wang, Y.-Z. (2020). Flame Retardation of Natural Rubber: Strategy and Recent Progress. Polymers, 12(2), 429. https://www.mdpi.com/2073-4360/12/2/429

Wik, A. and Dave, G. (2006). Acute toxicity of leachates of tire wear material to Daphnia magna—Variability and toxic components, *Chemosphere* 64(10), 1777–1784. https://doi.org/10.1016/j.chemosphere.2005.12.045

Wik, A. and Dave, G. (2009). Occurrence and effects of tire wear particles in the environment – A critical review and an initial risk assessment, *Environmental Pollution* 157(1), 1–11. https://doi.org/10.1016/j.envpol.2008.09.028

Wik, A., Nilsson, E., Källqvist, T., Tobiesen, A. and Dave, G. (2009). Toxicity assessment of sequential leachates of tire powder using a battery of toxicity tests and toxicity identification evaluations. *Chemosphere* 77(7), 922–927. https://doi.org/10.1016/j.chemosphere.2009.08.034

Winther, M and Slentø, E. 2010. *Heavy Metal Emissions for Danish Road Transport*. Neri Technical Report, no. 780, National Environmental Research Institute, Aarhus University. *http://www.dmu.dk/Pub/FR780.pdf*. Aarhus, Denmark: National Environmental Research Institute.

Yang, K., Jing, S., Liu, Y., Zhou, H., Liu, Y., Yan, M. *et al.* (2022). Acute toxicity of tire wear particles, leachates and toxicity identification evaluation of leachates to the marine copepod, Tigriopus japonicus. *Chemosphere* 297, 134099. https://doi.org/10.1016/j.chemosphere.2022.134099

Zhang, H.-Y., Huang, Z., Liu, Y.-H., Hu, L.-X., He, L.-Y., Liu, Y.-S., *et al.* (